



## TECHNICAL PRODUCT INFORMATION

Product: White over winter 50% shade  
Catalog Number: E1449  
UV Resistance 10 months at 120 KLy  
Width: Up to 14.5 m  
Length: According to customer order

Property	Units	3 mil	4 mil	5 mil
Tensile Strength at break[MD]	MPa.	24	24	24
Tensile Strength at break[TD]	MPa.	24	24	24
Elongation at break [MD]	%	700	700	700
Elongation at break [TD]	%	700	700	700
Tear resistance[MD]	gr/mil	250	250	250
Tear resistance[TD]	gr/mil	250	250	250
Falling Dart Impact	gr.	500	600	700
Total light transmission	%	50	50	48
Light diffusion	%	55	55	55
Thermicity	%	NA	NA	NA
Thickness average	%	±5% on nominal		
Thickness tolerance	%	±15%		

All statements, information and data given herein are believed to be accurate and reliable, but are presented without warranty and liability of any kind, express or implied. Statement or suggestion concerning possible use of our products are made without representation or warranty that any such use is free of patent infringement, and are not a recommendation to infringe any patent. The user should not assume that all safety measures are indicated, or that other measures may not be required.

## **Use and limitation:**

- **Exposure to chemicals:** exposure of greenhouse films to severe chemical conditions has an adverse effect on the lifetime of the film. Avoid excessive use of agrochemicals such as pesticides, herbicides, fungicides and fertilizers. Take measures to prevent direct contact of chemicals to the film. Ensure that metal structures are galvanized and are free from corrosion. When wooden structure parts are used, avoid contact of the film with resin, oil, petroleum or volatile preservatives. Prevent contact of the film with PVC accessories. Chemicals containing halogens, sulfur, copper, iron, are known to accelerate the degradation of greenhouse films.

**Specifically, if the following elements are found at levels higher than specified, the films are excluded from this warranty:**

**Sulfur: max 100 ppm, Chlorine: 0 ppm, Iron: 50 ppm**

- **Overheating:** the film has an adverse effect on its lifetime. Hot air should be directed away from the film.
- **Disinfection chemical use:** when chemicals are used to disinfect the soil, the treated soil must be covered with a film for a minimum of three weeks. After the film is removed, the greenhouse should be ventilated.